Orton
www.ortonceramic.com

Materials Testing and Research Center

6991 Old 3C Highway
Westerville, OH 43082, USA

Phone: 800-999-5442 x1323
Fax: 614-895-5610

ASTM C598
Annealing and Strain Point of Glass by Beam Bending

NIST Calibration Glass: 716
NIST Annealing Point (°C): 577
NIST Strain Point (°C): 533

Customer: Molten Aura Labs

Sample ID	Gold Ruby					
Color / Form	Pink / 1/4" Cane					
	Run Number					
	1	2	3	4	5	Average
Breadth (mm)	3.26	3.26	3.29	3.22	3.22	
Depth (mm)	3.26	3.21	3.16	3.23	3.23	
Load (g)	881	867	878	839	839	
Annealing Point (°C)	564	566	562	564	565	564
Strain Point (°C)	512	517	508	510	511	512